

INTERNATIONAL GRADE COMPARISONS AND CHEMICAL ANALYSIS

AA International Designation	Canada	France	Germany	Switzerland	United Kingdom (Prior to 1983)	Formerly used in South Africa
Unalloyed Aluminium						
1050A	—	A5	Az 99,5	Az 99,5	1B	1S
1070A	—	A7	Az 99,7	Az 99,7	—	HP
1100	1100	A45	—	—	—	D25
1145	—	—	—	—	—	E1S
1200	1200	A4	Az 99	Az 99	1C	2S
1350	1350	—	—	—	—	C1S
Aluminium-Copper Alloys						
2011	2011	A-U5PbBi	Az CuBiPb	Az Cu6BiPb	FC1	28S
2014A	—	—	—	—	—	B26S
2017A	—	A-U4G	Az CuMg1	—	—	17S
2024	2024	A-U4G1	Az CuMg2	Az Cu4Mg 1,5	2L97 L98	24S
2030	—	A-U4Pb	—	—	—	T1701
Aluminium-Manganese Alloys						
3003	3003	A-M1	Az MnCu	Az Mn	—	D3S
3004	—	A-M1G	Az Mn1Mg1	—	—	D4S
3005	—	A-MG),5	Az Mn1Mg0,5	—	—	C4S
3103	—	—	Az Mn	—	N3	3S
3105	—	—	Az Mn0,5Mg0,5	—	N31	E4S
Aluminium-Magnesium Alloys						
5050	—	A-G1,5	—	Az Mg1,5	—	A57S
5052	5052	A-G2,5C	Az Mg2,5	—	—	57S
5083	5083	A-G4,5MC	Az Mg4,5Mn	Az Mg4,5Mn	N8	D54S
5154A	—	—	—	—	N5	54S
5182	—	—	—	—	—	F54S
5251	—	A-G2M	Az Mg2Mn0,3	Az Mg2,5	N4	M57S
5454	5454	A-G2,5MC	Az Mg2,7Mn	Az Mg2,7Mn	N51	B53S
5657	—	—	—	—	—	L57S
Aluminium-Magnesium-Silicon Alloys						
6005	—	—	—	—	—	C51S
6063	6063	—	—	—	H9	50S
6070	—	—	—	—	—	6070
6082	—	A-SGM0,7	Az MgSi1	Az MgSi1Mn	H30	B51S
6101A	—	—	—	—	91E	D50S
6261	6261	—	—	—	H20	D65S
6463	—	—	—	—	E6	C50S
Aluminium-Zinc Alloys						
7020	—	A-Z5G	—	Az Zn4,5Mg1	H17	D74S
7075	7075	A-Z5GU	Az ZnMgCu1,5	Az Zn6MgCu1,5	2L88	T7502
Aluminium-Other Element Alloys						
8011	—	A-FeS	Az FeSi	—	—	98S
8006	—	—	—	—	—	8006